



LABELS DIRECT

Thermal Transfer Ribbons



TR4085plus™ Premium Resin-Enhanced Wax

Product Description

The industry's leading wax product since its introduction to the market in November 2000, TR4085plus™ features our SmoothCoat® backcoat with a 4 Million Linear Inch Guarantee. This unique ink formulation dissipates static and is versatile enough to print on a wide variety of label stocks. No other wax product beats TR4085plus™ when it comes to Edge Definition™ for crisp, rotated bar codes and dark, durable images.

Recommended Applications



FLEXIBLE
PACKAGING



GENERAL



INVENTORY



LOGISTICS



PARTS
PACKAGING



PHARMACEUTICAL



PRODUCT ID



RETAIL



RFID



SHELF



SHIPPING



SIGNAGE

Recommended Substrates

Coated/uncoated paper & tag stocks, synthetic paper, polyethylene, polypropylene, polyolefin, Kimdura®, Valeron®, Polyart®, gloss paper, flood-coated paper, UV varnished labels

Performance Characteristics

- Prints on a wide variety of substrates from uncoated papers to mid-range synthetic films
- Prints at high speeds (12 IPS) delivering crisp, rotated bar codes
- Dissipates static
- Enhanced smudge and scratch resistance
- Superior print quality on flood-coated labels
- Unbeatable Edge Definition™ for dark, dense images and improved scan rates

Visit us at www.labelsdirect.com

Labels Direct, Inc.

664 Trade Center Blvd.
Chesterfield, MO 63005
Phone Support: 636-458-5156
Toll Free Support: 800-458-5110
Fax: 636-458-5693



LABELS DIRECT



Thermal Transfer Ribbons

TR4085plus™ Premium Resin-Enhanced Wax

Ribbon Properties

Description	Result	Test Method
Ink	Wax (resin-enhanced)	
Color	Black	Visual
Total Thickness	8.0 ± 0.5µ	Micrometer
Base Film Thickness	4.8 ± 0.3µ	Micrometer
Ink Thickness	3.2 ± 0.2µ	Micrometer
Ink Melting Point	75°C (167°F)	Differential Scanning Calorimeter

Durability of Printed Image

Label Stock: Coated Paper

Print Speed: 6 IPS

Description	Result	Test Method
Print Density	> 1.80	Densitometer
Smudge Resistance	A*	Colorfastness Tester - 50 Cycles @ 500 Grams with Cotton Cloth
Scratch Resistance	A*	Colorfastness Tester - 20 Cycles @ 200 Grams with Stainless Steel Pointed Tip

*American National Standard Institute (ANSI) Grade Levels A, B, C, D, and F, where A is excellent, B is above average, C is average, D is below average, and F is poor.

Conversion Chart

Millimeters (mm) to Inches = mm ÷ 25.4	Inches to Millimeters (mm) = Inches ÷ 0.03937
Meters (m) to Feet (ft) = m ÷ 0.3048	Feet (ft) to Meters (m) = Feet ÷ 3.2808
C° to F° = (1.8 X C°) + 32 = F°	F° to C° = (F° ÷ 1.8) - 17.77
Thousand square inches (MSI) to m ² = MSI X 0.645	MSI = m ² ÷ 0.645

The information on this data sheet was obtained in our laboratories. Measured values may vary slightly when tested in a different environment. Information contained within this document is subject to change without notification.

Visit us at www.labelsdirect.com

Labels Direct, Inc.

664 Trade Center Blvd.

Chesterfield, MO 63005

Phone Support: 636-458-5156

Toll Free Support: 800-458-5110

Fax: 636-458-5693